



CORE DIMENSIONS					
UNCOATED CORE				28T0135-000	
	MM	INCHES		MM	INCHES
OD	3.43	(.135)	±	.13	(.005)
ID	1.78	(.070)	±	.13	(.005)
TH	1.27	(.050)	±	.13	(.005)
SINGLE PARYLENE COATING				28T0135-00P	
OD	3.45	(.136)	±	.13	(.005)
ID	1.75	(.069)	±	.13	(.005)
TH	1.30	(.051)	±	.13	(.005)

INITIAL PERMEABILITY 850  
WEIGHT / K 0.09 LBS

ELECTRICAL SPECIFICATION								
	MIN ( $\mu$ H)	MIN TOL.	NOM ( $\mu$ H)	MAX ( $\mu$ H)	MAX TOL.	FREQ. (kHz)	VOLT. (V)	URNS
L	.113	(-20%)	.142	.170	(+20%)	100	$\leq$ .00045	1
Q	REF	-	-	-	-	100	$\leq$ .00045	1
NET IMPEDANCE	MIN ( $\Omega$ )	TOL	NOM ( $\Omega$ )			FREQ. (MHz)		URNS
Z1 (REF.)	4.48	(-25%)	5.97	-	-	25	-	1
Z2	8.46	(-25%)	11.28	-	-	150	-	1

COATING SPECIFICATIONS				
	TYPE	coating thickness (mils.)	Min. DLB VAC	TEST FORCE (LB)
28T0135-000	UNCOATED	-	-	-
28T0135-00P	PARYLENE	0.5	1000	.10

NOTES:



Rev	Description	Date	INT
A	Original Draft	7/7/1995	JBE
B	UPDATED TO NEW FORMAT	7/7/1995	JBE
C	UPDATED ELECT & Z SPECS	5/6/1996	BAC
D	TRANSFER TO LOTUS NOTES	11/12/1997	IS
E	REVISED GAUSS TO 10	12/17/2003	TPM
F	REM Q SPECS CHANGE PART NUMBER	9/30/2005	JRK
G	REVISED TEMPLATE	4/5/2006	WMM

Date: 4/5/06	DWG # 28T0135-00P-G	Rev: G
Drawn By: WMM	Title # 28T0135-00P-	

Steward This document contains information which is proprietary to Steward. No production or publication of this document in whole or in part shall be made without written authorization from Steward.

UNCONTROLLED DOCUMENT