

Thermally Conductive Insulators



THICKER THERMAL INSULATOR PAD PREVENTS ELECTRICAL SHORTS IN AUTOMOTIVE ELECTRONICS APPLICATIONS

Tgard[™] 500 is a medium thermal performance insulator pad consisting of a ceramic filled, high temperature, silicone rubber coated on electrical grade fiberglass. Tgard[™] 500 has proven low thermal resistance after reliability and shows no delamination.

Tgard[™] 500 is designed for applications that require additional thickness to prevent electrical shorts from stamped aluminum heatsinks used in switching mode power supplies (SMPS) and debris from aluminum castings used in automotive motor controls.

FEATURES AND BENEFITS

- High breakdown voltage of > 6,000 volts AC
- Thermal resistance of 0.48° Cin2/watt at 50 psi
- Thermal resistance of 0.28° Cin2/watt at 400 psi
- Thick enough to encapsulate burrs of stamped heatsinks

APPLICATIONS

- Automotive motor controls
- Switching mode power supplies
 - stamped aluminum heatsinks





Thermally Conductive Insulators

PROPERTIES	TEST METHOD		METRIC VALUES		ES I	IMPERIAL VALUES	
ELECTRICAL PROPERTIES							
Dielectric with standard voltage 50mm probe for 30 sec	ASTM D149		4,500 volts AC			4,500 volts AC	
Dielectric breakdown voltage 50mm probe	ASTM D149		Avg >6,000 volts AC			Avg >6,000 volts AC	
Volume resistivity	ASTM D257 10 ¹² ohm-cm			10 ¹² ohm-in			
Dielectric constant @1Mhz	ASTM [0150	3.3			3.3	
Electrical RTI temperature rating	UL746D 150ºC			302ºF			
MECHANICAL PROPERTIES							
Thickness			0.23 mm			0.009 in	
Hardness	ASTM D2240		80 Shore A			80 Shore A	
Tensile strength	ASTM D412		11.7 Mpa			1.7 Kpsi	
Elongation @ 45º to warp/fill	ASTM D412		20%			20%	
Elongation along width or length	ASTM D412		5%			5%	
Operating temperature range			-60º to 180ºC		-	-76º to 356ºF	
Color			Brown			Brown	
UL flammability rating	UL 94		V-0			V-0	
PRESSURE	UNITS	10 (69)	25 (172)	50 (345)	100 (689)	200 (1379)	400 (2758)

TOTAL THERMAL RESISTANCE Modified ASTM D5470 °C-in²/watt 0.81 0.70 0.48 0.30 0.28 0.33 Modified ASTM D5470 °C-cm²/watt 5.16 3.21 2.13 1.80

USA: +1.866.928.8181 Europe: +49.8031.24600

Asia: +86.755.2714.1166

www.laird.com



Standard thickness: 9 mils (0.229 mm)

Configurations available: • Sheet form, roll form and die-cut parts

· Single-side, pressure-sensitive adhesive on request

• Without adhesive (A0): 12 x 18" sheets, 12" x 65M, Standard options:

12" x 30M roll or custom configuration

• With adhesive (A1): 11.75 x 18" sheets, 11.75" x 30M roll or custom configuration

Data for design engineer guidance only. Observed performance varies in application. Engineers are reminded to test the material in application.