



PRODUCT DESCRIPTION

Tpcm™ 5000 is a new high-performance TIM in the Laird product offering. Tpcm™ 5000 is designed to provide the best performance to price available. Tpcm™ 5000 provides very low thermal resistance by coupling high thermal conductivity of 5.3 W/mK, minimal bondline thickness, and with superior wetting of the mating surfaces. Softening between 50°C – 70°C, the initial pad thickness can decrease to a bondline as thin as 25µm.

Tpcm™ 5000 reliability has been demonstrated through exposure to 1000 hours of various aging tests resulting in proven dependability at an operating temperature of 125°C.

The specialty polymeric matrix offers superior pump out resistance when compared to thermally conductive greases and other phase change materials. Tpcm™ 5000 has been formulated to provide just the right tack, remaining on liners yet easily removeable for application.

FEATURES & BENEFITS

- 5.3 W/mK bulk thermal conductivity
- Cost effective
- Non silicone formulation that provides naturally tacky surface
- Fully characterized long term reliability
- No pump out
- Easy rework

MARKETS

- Semiconductor Packaging
- Graphics Card
- Notebooks
- Servers
- IGBTs
- Automotive
- Memory Modules
- Game Consoles

AVAILABILITY

- Four thickness: 0.125mm, 0.2 mm, 0.25mm, 0.4mm (Tpcm 5125, Tpcm 5200, Tpcm 5250, Tpcm 5400 respectively)
- Sheets and Die Cuts, Die cut on strips w/tabs, Die cut on rolls w/tabs
- Designed for use with the TIM Print, Refer to "TIM Print Application Guide"

STORAGE CONDITIONS

- Shelf life: 1 year from date of shipment in sealed bag
- Storage conditions: 0 to 40C in sealed bag. No humidity requirements.
- See A18223-00 "Instruction for Use" for more details

TYPICAL PROPERTIES

PROPERTY	VALUE	TEST METHOD
Construction	Free Standing, Filled, Non-Silicone Thermoplastic	N/A
Color	Grey	Visual
Thickness & Tolerance	0.125mm±0.025mm 0.200mm±0.025mm 0.250mm±0.025mm 0.400mm±0.050mm	
Density	2.6 g/cc	Helium Pycnometer
Bulk Thermal Conductivity	5.3 W/m-K	Hot Disk
Thermal Resistance		
10 psi & 70°C (Tpcm 5125)	0.20°C-cm ² /W	ASTM D5470
50 psi & 70°C	0.10°C-cm ² /W	
Operating Temperature Range	-40°C to 125°C	Laird Test Method
Softening Temperature Range	50°C to 70°C	Laird Test Method
Minimum Bondline Thickness	25µm	Laird Test Method
Dielectric Constant	31.2 @ 1MHz	ASTM D150
Volume Resistivity	1.4X10 ¹⁴ Ω-cm	ASTM D991
UL Recognition	V-0	UL94

USA: +1.866.928.8181

Europe: +49.8031.24600

Asia: +86.755.2714.1166

www.laird.com



THR-DS-Tpcm 5000-01302024

Any information furnished by Laird Technologies, Inc. or any of its affiliates or agents ("Laird") is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird materials rests with the end user. Laird makes no warranties as to the fitness, merchantability, suitability or non-infringement of any Laird materials or products for any specific or general uses. Laird shall not be liable for incidental or consequential damages of any kind. All Laird products are sold pursuant to the Laird's Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2022 Laird Technologies, Inc. All Rights Reserved. Laird™, Laird Technologies™, the Laird Logo, and other marks are trademarks or registered trademarks of Laird Technologies, Inc. or an affiliate company thereof. DuPont™ is a trademark or registered trademark of DuPont de Nemours, Inc. or an affiliate company thereof. Other marks may be owned by third parties. Nothing herein provides a license under any Laird or any third-party intellectual property rights.