**NuSil Technology LLC**
1050 Cindy Lane
Carpinteria, CA 93013
**t** +1 (805) 684 8780

# Test Report for
## Mass Loss and Collected Volatile Condensable Materials

Customer: LAIRD TECH
4707 DETROIT AVENUE
CLEVELAND
44102
Attention: DEVIN GALLAGHER

Order #: 10016770
TR #: 36426
P.O. #: 295490

Sample #: 28653
Material Tested: TPCM7000 PLUS
Test Date: 6/6/2025
Instrument #: 1714
Test Number: 5788

Test Temperature (°C): 125
Lot #: N/A
Pressure (torr): 5.1XE-7
Material Description: GRAY RUBBER

| | Specification Limits | Results (%) | Detection Limits (%) | Number of Replicates |
|---|---|---|---|---|
| Total Mass Loss (TML) | 1.00% maximum | 0.33 | 0.01 | 3 |
| Collected Volatile Condensable Material (CVCM) | 0.10% maximum | 0.13 | 0.01 | 3 |
| Water Vapor Recovered (WVR) | Report | 0.01 | 0.01 | 3 |

Comments: N/A

Specimen Appearance After Test: N/A

Testing performed in accordance with ASTM E595-15 (2021)

Report approved by: Suzanne Steiner Date: June 09, 2025
Quality Assurance Designate