



Laird™ Eccosorb™ JW0611

Magnetically loaded, elastomeric microwave absorber

Description

Laird™ Eccosorb™ JW0611 is a silicone based magnetic loaded absorber sheet, engineered to minimize or potentially eliminate surface currents, cavity resonance and coupling across 6GHz to 11GHz frequency range.

By lowering the quality factor (Q) of cavities, Laird™ Eccosorb™ JW0611 enhances the operation of microwave devices. Its tighter thickness tolerance control can also help to achieve -8dB reflectivity within the designated frequency range.

Typical properties	Test method	Typical value
Effective frequency range		6 to 11GHz
Resin		Silicone
Color		Grey
Hardness	ASTM D2240	80 shore A
Tensile strength	ASTM D412	3.8 MPa
Elongation @ break	ASTM D412	100%
Thickness without pressure sensitive adhesive (PSA)		1.335mm ±0.075mm
Working temperature		-40 to 125°C
Volume resistivity	ASTM D257	1x10 ¹³ Ohm.cm
Outgassing (%TML/%CVCM)	ASTM E595	0.2/0.06
Flame retardance	UL 94	V0

Note: Data for design engineer guidance only. Observed performance varies in application. Engineers are reminded to verify the material in application.

Features and benefits

- Fine-tuned parameter for good reflectivity at 6GHz to 11GHz
- High thermal stability
- Electrically non-conductive
- Good mechanical strength
- RoHS compliant


Applications

- Data center
- Microwave transmitter/receivers
- Automotive
- Aerospace and defense


Availability

- Standard sheet size is 305 x 305mm (12"x12").
- Part Number: A19065-0526-01
- It can be supplied with or without PSA.
- Other thicknesses, sizes, and customer-specified shapes can be available upon request.

Graph 1: Attenuation



Graph 2: Reflectivity



Limitations

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

Health and environmental information

To support customers in their product safety needs, Qnity has an extensive product stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area. For further information, please see our website, www.qnityelectronics.com, or consult your local Qnity representative.

For more information on Laird™ Eccosorb™ JW0611 absorber sheet or other Qnity products, please visit our website, www.qnityelectronics.com.

The information set forth herein is furnished free of charge, is based on technical data that Qnity believes to be reliable, and represents typical values that fall within the normal range of properties. This information reflects our knowledge of the subject at the date of publication and may be subject to revision. This information relates only to the specific material designated and may not be valid for such material used in combination with other materials or in other processes. It is intended for use by persons having technical skill, at their own discretion and risk. This information should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards and comply with applicable law. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

CAUTION: Do not use Qnity materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been approved by Qnity for such use in accordance with the Qnity Medical Applications Policy. Please ask your Qnity representative for a copy of the current Qnity Medical Applications Policy and further guidance.

Qnity's sole warranty is that our products will meet our standard sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, QNITY SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, OR NON-INFRINGEMENT. QNITY DISCLAIMS LIABILITY FOR ANY SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES.



© 2026 Qnity Electronics, Inc. All rights reserved. Qnity™, the Qnity Node Logo and all trademarks and service marks designated with ™, SM or ® are owned by affiliates of Qnity Electronics, Inc. unless otherwise noted.

Rev (01/26)